

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA
VAT No. LV 43603022749
Dobeles iela 41, Jelgava, LV-3001, Latvia
Phone +371 63010605 * E-mail meka@e-koks.lv * Web www.e-koks.lv

Classification of reaction to fire performance in accordance with EN 13501-1:2007+A1:2009

Issue number: K31/2017

Date of issue: 21.09.2017.

Sponsor: Van de Sande BV.

Address: Den Uitvanck 12A, 5688XG, Oirschot, Holland.
Reg. No. 819151889B01.

Owner of classification report: Van de Sande BV.

Address: Den Uitvanck 12A, 5688XG, Oirschot, Holland.
Reg. No. 819151889B01.

Manufacturer: Building Innovations Ltd.

Prepared by: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*).

Product name: SANCOUSTIC_Mineral Wool.

Laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATPAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316. Laboratory is a notified body with reg. No. NB 2040 under construction product regulation No. 305/2011.

Classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, excepted with the prior written approval of the Forest and Wood Products Research and Development Institute

1. Introduction

This classification report defines the reaction to fire classification assigned to building insulation system SANCOUSTIC_Mineral Wool in accordance with the procedures given in EN 13501-1:2007+A1:2009.

2. Details of classified product

2.1. General

SANCOUSTIC_Mineral Wool is defined as a thermal insulation system for buildings. System is not described by harmonized European technical specification. Insulation material mineral wool (MW) is defined as Thermal insulation products for buildings - Factory made mineral wool (MW) products according standard EN 13162:2012+A1:2015. SANCOUSTIC WoodWool is defined as Thermal insulation products for buildings - Factory made wood wool (WW) products according standard EN 13168:2012+A1:2015.

2.2. Product description

- Product name: SANCOUSTIC_Mineral Wool.
- Manufacturer: Building Innovations Ltd.
- Materials used for manufacturing:
 - SANCOUSTIC WoodWool (Wood wool, white cement, liquid glass with product thickness 25 mm, weight 375 kg/m³;
 - Mineral wool insulation with 50 and 150 mm thickness and density 65 kg/m³.
- Insulation system total thickness tested: 75 and 175 mm.

3. Test reports and test results in support of classification

3.1. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Van de Sande BV.	2501-1/2017	EN 13823:2010+A1:2014
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Van de Sande BV.	2501-2/2017	EN ISO 11925-2:2010

2. Test results

2. Test results				
Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2010+A1:2014	$FIGRA_{0,2MJ}(W/s)$	4	50.7	Compliant
	$FIGRA_{0,4MJ}(W/s)$		39.8	(-)
	$THR_{600s}(MJ)$		3.3	Compliant
	LFS		<1000 mm	Compliant
	$SMOGRA(m^2/s^2)$		Threshold not reached	Compliant
	$TSP_{600s}(m^2)$		25.1	Compliant
EN ISO 11925-2:2010	Flaming droplets <10s	24	no	Compliant
	Flaming droplets >10s		no	Compliant
	Flame spread (Fs)		Less than 150 mm	Compliant
	Ignition of filter paper		no	(-)
	Flaming droplets/particles		no	(-)
	Exposure time 30 s. Test duration 60 s.			
(-) not applicable				

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2007+A1:2009.

4.2. Classification

SANCOUSTIC_Mineral Wool in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

Reaction to fire classification: B-s1-d0

4.3. Field of application

4.3.1 This classification is valid for the following product end use applications:

Product primary is intended to use as insulation system for buildings.

4.3.2. This classification is also valid for following product parameters:

Thickness of product:	Valid only for SANCOUSTIC WoodWool panel thickness 25 mm. valid for MW insulation thickness 50 mm and higher thicknesses.
Composition of product:	valid only for product composition as tested.
Structure of product:	valid only for product structure as tested.
Product density:	valid for product density within limits $\pm 15\%$ as tested.

4.3.3. Classification valid for installation parameters:

Mounting:	product tested without air gap between wood wool boards and insulation material.
Substrates:	product performance determined with gypsum plasterboard substrate and classification is valid for product mounting on substrates of reaction to fire class A1 and A2-s1-d0.
Joints:	product tested with horizontal and vertical joints, and classification is valid for any joint arrangements.
Orientation:	not applicable.
Fixings:	valid for elements fixed with metal fixings.

5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.



Prepared by

E. Bukšāns

(signature)

Reviewed by

K.Būmanis

(signature)